



**GEOTEX 106F** is a woven monofilament polypropylene fabric produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The individual filaments are woven into a regular network and calendared such that filaments retain dimensional stability relative to each other. These characteristics make **GEOTEX 106F** ideal for filtration beneath hard armor systems. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 106F** conforms to the property values listed below.<sup>1</sup> Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

MARV<sup>2</sup>

PROPERTY	TEST METHOD	ENGLISH	METRIC
----------	-------------	---------	--------

**ORIGIN OF MATERIALS**

% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%

**MECHANICAL**

Tensile Strength (Grab)	ASTM D-4632	300 x 200 lbs	1335 x 890 N
Elongation	ASTM D-4632	15 x 15%	15 x 15%
CBR Puncture	ASTM D-6241	850 lbs	3782 N
Trapezoidal Tear	ASTM D-4533	65 x 65 lbs	289 x 289 N

**ENDURANCE**

UV Resistance % Retained at 500 hrs	ASTM D-4355	90%	90%
--	-------------	-----	-----

**HYDRAULIC**

Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	40 US Std. Sieve	0.425 mm
Percent Open Area	CW-02215 MOD. <sup>4</sup>	6%	6%
Permittivity	ASTM D-4491	0.5 sec <sup>-1</sup>	0.5 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	35 gpm/ft <sup>2</sup>	1426 lpm/m <sup>2</sup>

ROLL SIZES		12 ft x 330 ft	3.65 m x 100.6 m
------------	--	----------------	------------------

**NOTES:**

1. The property values listed above are effective 04/2011 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average e roll value.
4. Army Corp of Engineers test method correlated to light emitted through fabric. (Area of Openings/Total Area X 100%)

