

PRODUCT DATA SHEET

GEOTEX® 351

GEOTEX 351 is a polypropylene, staple fiber, needlepunched nonwoven geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The fibers are needled to form a stable network that retains dimensional stability relative to each other. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX 351 conforms to the property values listed below.¹ Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	MARV ²	
		ENGLISH	METRIC
Mechanical			
Tensile Strength (Grab)	ASTM D-4632	95 lbs	423 N
Elongation	ASTM D-4632	50%	50%
Puncture	ASTM D-4833	55 lbs	245 N
CBR Puncture	ASTM D-6241	260 lbs	1157 N
Mullen Burst	ASTM D-3786	185 psi	1275 kPa
Trapezoidal Tear	ASTM D-4533	40 lbs	178 N
Endurance			
UV Resistance % Retained at 500 hrs	ASTM D-4355	70%	70%
Hydraulic			
Apparent Opening Size (AOS) ³	ASTM D-4751	50 US Std. Sieve	0.300 mm
Permittivity	ASTM D-4491	2.00 sec ⁻¹	2.00 sec ⁻¹
Water Flow Rate	ASTM D-4491	150 gpm/ft ²	6112 l/min/m ²
Roll Sizes		12.5 ft x 360 ft 15 ft x 360 ft	3.81 m x 109.8 m 4.57 m x 109.8 m

NOTES:

1. The property values listed above are effective 06/2009 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.



THE ADVANTAGE CREATORS.™

Propex Operating Company, LLC PH: 423 899 0444
6025 Lee Highway, Suite 425 PH: 800 621 1273
PO Box 22788 FAX: 423 899 7619
Chattanooga, TN 37422 www.geotextile.com

Geotex®, Landlok®, Pyramat®, X3®, SuperGro®, Petromat® and Petrotac® are registered trademarks of Propex Operating Company, LLC.

THIS PUBLICATION SHOULD NOT BE CONSTRUED AS ENGINEERING ADVICE. WHILE INFORMATION CONTAINED IN THIS PUBLICATION IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, PROPEX DOES NOT WARRANT ITS ACCURACY OR COMPLETENESS. THE ULTIMATE CUSTOMER AND USER OF THE PRODUCTS SHOULD ASSUME SOLE RESPONSIBILITY FOR THE FINAL DETERMINATION OF THE SUITABILITY OF THE INFORMATION AND THE PRODUCTS FOR THE CONTEMPLATED AND ACTUAL USE. THE ONLY WARRANTY MADE BY PROPEX FOR ITS PRODUCTS IS SET FORTH IN OUR PRODUCT DATA SHEETS FOR THE PRODUCT, OR SUCH OTHER WRITTEN WARRANTY AS MAY BE AGREED BY PROPEX AND INDIVIDUAL CUSTOMERS. PROPEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ARISING FROM PROVISION OF SAMPLES, A COURSE OF DEALING OR USAGE OF TRADE.