



GEOTEX 3X3HF is a woven polypropylene geotextile containing heavy monofilament/ fibrillated yarns produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. These characteristics make **GEOTEX 3X3HF** ideal for the construction of embankments over soft soils, steepened slopes, and modular block and/or wrapped-face retaining walls. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments for normally found in soils.

GEOTEX 3X3HF conforms to the property values listed below.¹ Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

MARV²

PROPERTY	TEST METHOD	ENGLISH	METRIC
----------	-------------	---------	--------

ORIGIN OF MATERIALS

% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%

MECHANICAL

Tensile Strength (Grab)	ASTM D-4632	450 x 350 lbs	2002.5 x 1557.5 N
Elongation	ASTM D-4632	15 x 6%	15 x 6%
Wide Width Tensile	ASTM D-4595	3600 x 3600 lbs/ft	52.6 x 52.6 kN/m
Wide Width Elongation	ASTM D-4595	15 x 10%	15 x 10%
Wide Width Tensile at 2% Strain	ASTM D-4595	480 x 420 lbs/ft	7.0 x 6.1 kN/m
Wide Width Tensile at 5% Strain	ASTM D-4595	1392 x 1740 lbs/ft	20.3 x 25.4 kN/m
Wide Width Tensile at 10% Strain	ASTM D-4595	3180 x 3480 lbs/ft	46.4 x 50.8 kN/m
CBR Puncture	ASTM D-6241	1600 lbs	7120 N
Trapezoidal Tear	ASTM D-4533	180 x 140 lbs	801 x 623 N

ENDURANCE

UV Resistance % Retained at 500 hrs	ASTM D-4355	80%	80%
--	-------------	-----	-----

HYDRAULIC

Apparent Opening Size (AOS) ³	ASTM D-4751	30 US Std. Sieve	0.600 mm
Permittivity	ASTM D-4491	0.52 sec ⁻¹	0.52 sec ⁻¹
Water Flow Rate	ASTM D-4491	40 gpm/ft ²	1629.8 lpm/m ²

ROLL SIZES	12.5 ft x 360 ft 15.0 ft x 300 ft	3.81 m x 109.8 m 4.57 m x 91.5 m
------------	--------------------------------------	-------------------------------------

NOTES:

1. The property values listed above are effective 04/2011 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.



**GEOTEXTILE
SYSTEMS**
BY PROPEX

ENGINEERING EARTH
www.geotextile.com

Propex Operating Company, LLC · 6025 Lee Highway, Suite 425 · PO Box 22788 · Chattanooga, TN 37422

ph 423 899 0444 · ph 800 621 1273 · fax 423 899 7619

Geotex®, Landlok®, Pyramat®, X3®, SuperGro®, Petromat® and Petrotac® are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.