



**GEOTEX**<sup>®</sup> 4x1 is a structural soil reinforcement geotextile containing high tenacity polyester multifilament (warp) and polypropylene silt tape yarns (fill) produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The individual yarns are woven to form a strong geotextile. These characteristics make the **GEOTEX 4x1** ideal for the construction of steepened slopes and modular block and/or wrapped-face retaining walls. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 4x1** conforms to the property values listed below<sup>1</sup>. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP approved.

MARV <sup>2</sup>			
PROPERTY	TEST METHOD	ENGLISH	METRIC
<b>ORIGIN OF MATERIALS</b>			
% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%
<b>MECHANICAL</b>			
Tensile Strength (Grab)	ASTM D-4632	425 lbs	1891 N
Wide Width Tensile	ASTM D-4595	4800 lbs/ft	70 kN/m
Wide Width Elongation	ASTM D-4595	8%	8%
Wide Width Tensile Strength at 5% Strain	ASTM D-4595	1800 lbs/ft	26.3 kN/m
Long-term Design Strength (LTDS)	GRI-GT7	2272 lbs/ft	33.1 kN/m
Trapezoidal Tear	ASTM D-4533	170 lbs	757 N
<b>ENDURANCE</b>			
UV Resistance % Retained at 500 hrs	ASTM D-4355	N/A	N/A
<b>HYDRAULIC</b>			
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	30 US Std. Sieve	0.600 mm
Permittivity	ASTM D-4491	0.03 sec <sup>-1</sup>	0.03 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	2 gpm/ft <sup>2</sup>	81 l/min/m <sup>2</sup>
<b>ROLL SIZES</b>		7.5 ft x 300 ft	2.29 m x 91.5 m

**NOTES:**

1. The property values listed above are effective 04/2011 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.



**GEOTEXTILE  
SYSTEMS**  
BY PROPEX

ENGINEERING EARTH  
[www.geotextile.com](http://www.geotextile.com)

Propex Operating Company, LLC · 6025 Lee Highway, Suite 425 · PO Box 22788 · Chattanooga, TN 37422

ph 423 899 0444 · ph 800 621 1273 · fax 423 899 7619

Geotex<sup>®</sup>, Landlok<sup>®</sup>, Pyramat<sup>®</sup>, X3<sup>®</sup>, SuperGro<sup>®</sup>, Petromat<sup>®</sup> and Petrotac<sup>®</sup> are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.